



Self Leveling Underlayment Primer



Low VOC

Tile Perfect™ Self Leveling Underlayment (SLU) Primer works as a primer for Tile Perfect Self Leveling Underlayment.

- Multipurpose, one primer for all approved porous and non-porous substrates
- Easy to apply - up to 410 sq. ft. per gallon (10 m²/L)
- Dries to a transparent finish within 3 hours
- Enables installation of ceramic tile or natural stone directly to metal, gypsum underlayment, glazed tile (without scarifying) and well bonded epoxy coatings
- Solvent-free

Warranty

For details about our limited warranties, see your sales associate or www.hbfuller-cp.com/tp.

Suitable Substrates

Suitable for use over the following clean, dry, structurally sound and unpainted surfaces: concrete, cementitious backer units (CBU or cement board), exterior grade plywood, oriented strand board (OSB), adhesive residue (except tacky or pressure-sensitive adhesive), cold-rolled steel, existing ceramic tile, gypsum substrates-minimum tensile bond strength 72 psi (0.5 MPa), VCT or non-cushioned sheet goods if they are single layer only and well bonded to a substrate approved for tile. For specific recommendations on other substrates, please contact your Tile Perfect representative.

Product Specifications

Description	
Physical State	Acrylic emulsion
Open Time	Varies with temperature and humidity
Color	White, dries clear
Odor	Nil
Viscosity	Thin, liquid
Wt. per U.S. Gallon	8.8 lbs. ± 0.1 lb.
Wt. per Liter	1.06 kg ± 0.01 kg
Freeze/Thaw Stability	None. Do not freeze.

Limitations

Do not apply over wet areas. Do not use in areas subject to hydrostatic pressure. Not for use as a sealer. Do not use as a final wear surface.

Packaging

1 quart (946 ml) jug

Coverage

Substrates	Primer to Water Ratio	Coverage (sq. ft./gallon)
Porous Concrete (2 coats may be required for highly porous)	1:3	410
Gypsum Underlayments (two coats required, ratios 1:3 and 1:2)	1:3	410
Wood	3:1	250
Tile/Linoleum/Steel/ Concrete curing compounds	Full Strength	140

Surface Preparation

Remove all surface contaminants such as oil, grease, floor finishes, wax and dirt. Remove adhesive by scraping until all that remains is a thin, transparent layer of adhesive residue. For detailed substrate preparation information, refer to Tile Perfect Self Leveling Underlayment product data sheet.

Mixing Instructions

For best results, room and product should be kept at 50° to 70°F (10° to 21°C) for 24 hours before, during and 48 hours after application. Mix Tile Perfect SLU Primer in the ratios listed in the coverage chart.

Application Instructions

Use a paint brush, short nap roller or a soft push broom to apply in an even, continuous film. Do not allow product to puddle.

Drying Time

Tile Perfect SLU Primer typically dries in 1 to 3 hours and is transparent in color when dry. Cure times are based on 70°F (21°C) and 50% RH. Colder temperatures and higher humidity will extend cure times. Avoid excessive foot traffic and surface contamination.

Clean Up

Clean tools, hands and excess material immediately with water. Material that is cured is difficult to remove.

Cautions

FIRST AID MEASURES: In all cases, seek medical attention if symptoms develop or persist. EYES: Flush with water for 20 minutes. SKIN: Wash with soap and water. IF VAPORS INHALED: Remove to fresh air. IF SWALLOWED: Do not induce vomiting. WARNING! This product contains chemicals known to the State of California to cause cancer, birth defects or reproductive harm. KEEP OUT OF REACH OF CHILDREN. For Medical Emergency Information, call 1-888-853-1758.

SURFACE PREPARATION

Self Leveling Underlayment Primer

SURFACE PREPARATION

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered Tile Perfect brand product(s) under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

Storage/Shelf Life

DO NOT FREEZE; store in an unopened container in a cool, dry location out of direct sunlight and protected from weather. Maximum of 1 year from date of manufacture in unopened package.

Customer and Technical Services

Customer support

Toll Free: 800-832-9002

Fax: 800-952-2368

Technical assistance

Information is available by calling the Technical Support Hotline.

Toll Free: 800-832-9023

Fax: 630-952-1235



H.B. Fuller Construction Products Inc.

1105 South Frontenac Street
Aurora, IL 60504-6451 U.S.A.
www.hbfuller-cp.com/tp